

% OF RECYCLED CONTENTS IN THE STANDARD COLOURS + NEW COLOURS "LE PIETRE"

	Raw materials contained	Expressed in %	% of recycled material used
Sample : Bianco Carrara	White cement	20.8 %	Never recycled
	White marble powder	33.3 %	100 %
	White marble	45.9 %	100 %
	Average % of used recycled raw material = 79.2 %		
Sample : Botticino	White cement	20.8 %	Never recycled
	White marble powder	33.3 %	100 %
	Beige marble	45.9 %	100 %
	Average % of used recycled raw material = 79.2 %		
Sample : Grigio Perla	White cement	20.8 %	Never recycled
	White marble powder	33.3 %	100 %
	White marble	34.4 %	100 %
	Gray marble	11.5 %	0 %
	Average % of used recycled material = 67.7 %		
Sample : Grigio Bardiglio	White cement	20.8 %	Never recycled
	White marble powder	33.3 %	100 %
	White marble	34.4 %	100 %
	Gray marble	11.5 %	0 %
	Average % of used recycled material = 67.7 %		
Sample : Bianco Kristal	White cement	19.6 %	Never recycled
	White marble powder	31.4 %	100 %
	White marble	24.7 %	100 %
	Gray marble	16.5 %	0 %
	Black marble	7.8 %	0 %
	Average % of used recycled material = 56.1 %		
Sample : Grigio Barrè	White cement	19.6 %	Never recycled
	White marble powder	31.4 %	100 %
	White marble	24.7 %	100 %
	Gray marble	16.5 %	0 %
	Black marble	7.8 %	0 %
	Average % of used recycled material = 56.1 %		
Sample : Giallo Reale	White cement	20.8 %	Never recycled
	White marble powder	33.3 %	100 %
	Yellow marble	45.9 %	0 %
	Average % of used recycled material = 33.3 %		
Sample : Rosa Alicante	White cement	20.8 %	Never recycled
	White marble powder	33.3 %	100 %
	Red marble	45.9 %	100 %
	Average % of used recycled material = 79.2 %		
Sample : Rosso Verona	White cement	20.8 %	Never recycled
	White marble powder	33.3 %	100 %
	Red marble	45.9 %	100 %
	Average % of used recycled material = 79.2 %		
Sample : Rosa Perlino	White cement	20.8 %	Never recycled
	White marble powder	33.3 %	100 %
	Rosa marble	45.9 %	0 %
	Average % of used recycled material = 33.3 %		
Sample : Nero Marquinia	White cement	20.8 %	Never recycled
	White marble powder	33.3 %	100 %
	Black marble	45.9 %	0 %
	Average % of used recycled material = 33.3 %		
Sample : Veneziano 1	White cement	18.2 %	Never recycled
	White marble powder	29.1 %	100 %
	White marble	52.7 %	100 %
	Average % of used recycled material = 81.8 %		

Sample : Veneziano 4	White cement	18.2 %	Never recycled
	White marble powder	29.1 %	100 %
	Gray marble	52.7 %	100 %
	Average % of used recycled material = 81.8 %		
Sample : Veneziano 2	White cement	18.2 %	Never recycled
	White marble powder	29.1 %	100 %
	Beige marble	52.7 %	100 %
	Average % of used recycled material = 81.8 %		
Sample : Veneziano 6	White cement	18.2 %	Never recycled
	White marble powder	29.1 %	100 %
	Rosa marble	52.7 %	0 %
	Average % of used recycled material = 29.1 %		
Sample : Veneziano 3	White cement	18.2 %	Never recycled
	White marble powder	29.1 %	100 %
	Yellow marble	52.7 %	0 %
	Average % of used recycled material = 29.1 %		
Sample : Veneziano 5	White cement	18.2 %	Never recycled
	White marble powder	29.1 %	100 %
	Red marble	52.7 %	100 %
	Average % of used recycled material = 81.8 %		
Sample : Veneziano 9	White cement	18.5 %	Never recycled
	White marble powder	29.6 %	100 %
	White marble	16 %	100 %
	Gray marble	24.4 %	0 %
	Black marble	11.5 %	0 %
	Average % of used recycled material = 45.6 %		
Sample : Veneziano 8	White cement	18.5 %	Never recycled
	White marble powder	29.6 %	100 %
	White marble	16 %	100 %
	Gray marble	24.4 %	0 %
	Black marble	11.5 %	0 %
	Average % of used recycled material = 45.6 %		
Sample : Veneziano 10	White cement	18.2 %	Never recycled
	White marble powder	29.1 %	100 %
	Green marble	52.7 %	100 %
	Average % of used recycled material = 81.8 %		
Sample : Veneziano 7	White cement	18.5 %	Never recycled
	White marble powder	29.6 %	100 %
	Black marble	49.8 %	0 %
	White marble	2.1 %	100 %
	Average % of used recycled material = 31.7 %		
Sample : "Le Pietre" Dolomitica "Le Pietre" Lavica "Le Pietre" Basaltica "Le Pietre" Porfirica	White cement	25.0 %	Never recycled
	White powder marble	25.0 %	100 %
	Gray Silica-microgrit	50.0 %	100 %
	Average % of used recycled material = 75.0 %		
Sample : "Le Pietre" Artica "Le Pietre" Desertica	White cement	28.0 %	Never recycled
	White powder marble	23.0 %	100 %
	White Silica-microgrit	49.0 %	0 %
	Average % of used recycled material = 23.0 %		

Not considered in the above table and valid for all the samples :

-steel reinforcement : used steel containing about 40% of recycled raw material.

-ABS : used virgin ABS